

DTF TRANSFER RELEASE FILM (Cold peel matt film)

Suitable for inkjet digital printing by pigment ink, heat stabilized, shrinkage low, excellent printing outcome, highly matt effect, smooth peeling, scratch resistance, heat press temperature at 158 degrees and only need 15 seconds, antistatic treatment on the back.

Property	Unit	Method	Thickness 75u
Substance	g/m ²	internal(厂标)	108±3
Caliper	µm	internal(厂标)	75±5
Coating weight	g/m ²	internal(厂标)	12±1
Tensile strength (md)	Mpa	ASTM D 882	> 150
Tensile strength (td)	Mpa	ASTM D 882	> 150
Elongation at break (md)	%	ASTM D 882	> 80
Elongation at break (td)	%	ASTM D 882	> 70
Glossyness	%	ASTM D 882	< 15
Release	µm	internal(厂标)	< 3-4
Shrinkage (md) (180°C*1 minutes)	%	ASTM D 1204	< 1
Shrinkage (td) (180°C*1 minutes)	%	ASTM D 1204	< 0.5
Surface Resistivity (anti-static side)		ASTM D 257	< 10 ⁷

The above information is given in good faith and is generally reliable. However, the customer will have to examine the suitability of the film for individual application, hence no general or particular warranty for the applications for the film is offered by us. The above information is liable to change due to innovation and improvement in the manufacturing process. We assume no liability for any infringement of any patent, copyright or design on the part of the customer while exploiting the film for different end-users.

Eastman Kodak Company 343 State Street Rochester, NY 14650 USA +1-866-563-2533 in North America. Produced using Kodak Technology.
©Kodak, 2022 Kodak and the Kodak Logo are trademarks of Kodak. Subject to technical change without notice. W.PSD.XXX.0222.EN.1 (K-XXX)

KODAK.COM

